

21. A coating composition according to claim 20 wherein the wax content is about 18-22% by weight.

22. A coating composition according to claim 20 wherein the wax has a melting point in the range of 60-120°C.

23. A coating composition according to claim 20 wherein the wax has a melting point in the range of 60-90°C.

24. A coating composition according to claim 20 wherein the median particle size of the matting agent component is about 2 to 5 microns.

25. A coating composition according to claim 20 wherein the silica has a pore volume in the range of about 0.9 to about 1.2 cc/g.

26. A coating composition according to claim 20 wherein the radiation curable component comprises acrylates.

27. A coating composition according to claim 20 wherein the radiation curable component is curable by exposure to ultraviolet radiation.

28. A coating composition according to claim 20 wherein the radiation curable component is curable by electron beam radiation.

29. A coating composition according to claim 20 further comprising a curing initiator.

30. A coating composition according to claim 20 wherein the radiation curable component comprises acrylate and the coating composition comprises 2% by weight or less of matting agent component.

31. A coated substrate comprising a substrate and a coating thereon prepared from a composition according to claim 20.